



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] PG-0020N

- PP
- 20% Glass Fiber Reinforced
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	9672.83
Elongation	ASTM D638	%	4
Flexural Strength	ASTM D790	psi	13371.27
Flexural Modulus	ASTM D790	psi	574679.94
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.14
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	R-95
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	280.4
66 psi		°F	302
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
OTHER			
Density	ASTM D792	lb/in ³	0.0322
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ in/in	4-6
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	-
	UL-94	1/8 in	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			