



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] NG-1112B

- Nylon 6
- 12% Glass Fiber Reinforced/Impact Modified
- Black

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	12091.04
Elongation	ASTM D638	%	4
Flexural Strength	ASTM D790	psi	18349.93
Flexural Modulus	ASTM D790	psi	604551.92
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	2.57
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	R-114
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	374
66 psi		°F	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
OTHER			
Density	ASTM D792	lb/in ³	0.0368
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ in/in	4.3-5.3
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	-
	UL-94	1/8 in	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			