



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] NF-0040N

• Nylon 6 • 40% Mineral Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	900 (88.32)
Elongation	ASTM D638	%	1.5
Flexural Strength	ASTM D790	kg/cm ² (MPa)	1400 (137.39)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	9.00x10 ⁴ (8832.19)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	4.6 (45.1)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-116
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	-
(4.6kg/cm ²) (0.46MPa)		°C	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
OTHER			
Density	ASTM D792	g/cm ³	1.470
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ mm/mm	3.6-4.6
Moisture Contents	-	%	-
Flammability	UL-94	1.6mm	-
	UL-94	3.2mm	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			