



# NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399  
http://www.nytex.com.tw

## Product Information

## NYLOY<sup>®</sup> MG-0833B

• Nylon 66 • 33%Glass Fiber Reinforced • Black

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	kg/cm <sup>2</sup> (MPa)	1400 (137.39)
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	kg/cm <sup>2</sup> (MPa)	2000 (196.27)
Flexural Modulus	ASTM D790	kg/cm <sup>2</sup> (MPa)	8.0x10 <sup>4</sup> (7850.83)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	8.0 (78.43)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm <sup>2</sup> ) (1.82MPa)		°C	225
(4.6kg/cm <sup>2</sup> ) (0.46MPa)		°C	235
<b>ELECTRICAL</b>			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
<b>OTHER</b>			
Density	ASTM D792	g/cm <sup>3</sup>	1.380
Mold Shrinkage <sup>(2)</sup>	ASTM D955	x10 <sup>-3</sup> mm/mm	2-3
Moisture Contents	-	%	-
Flammability	UL-94	1.6mm	HB
	UL-94	3.2mm	-
<b>REMARK</b>			
<sup>(1)</sup> This data is for reference only.			
<sup>(2)</sup> Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			