



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] MG-8030N-V 60BK1

- Nylon 66
- 34% Glass Fiber Reinforced / Non-Halogen Flame Retardant
- Black

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	18492.18
Elongation	ASTM D638	%	1.3
Flexural Strength	ASTM D790	psi	26315.79
Flexural Modulus	ASTM D790	psi	1365576.1
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.1
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	455
66 psi		°F	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
OTHER			
Density	ASTM D792	lb/in ³	0.0448
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ in/in	-
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	V0
	UL-94	1/8 in	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			