

产品资讯

Product Information

NYLOY® NG-0033N-V0

• 尼龙6 • 33% 玻纤强化 / 阻燃级 • 本色

性质	PROPERTY	测试方法 METHOD	单位 UNIT	结果(数据) RESULT
机械性能	MECHANICAL			
抗张强度	Tensile Strength	ASTM D638	kg/cm ² (MPa)	1450 (142.3)
断裂伸长率	Elongation	ASTM D638	%	2
抗折强度	Flexural Strength	ASTM D790	kg/cm ² (MPa)	2050 (201.18)
抗折弹性系数	Flexural Modulus	ASTM D790	kg/cm ² (MPa)	9.52x10 ⁴ (9342.49)
冲击强度	IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	10.0 (98.04)
	IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
硬度	Hardness Rockwell R Scale	ASTM D785	-	R-117
	Hardness Shore D	ASTM D2240	-	-
热性能	THERMAL			
热变形温度	Heat Deflection Temp	ASTM D648		
	(18.6kg/cm ²) (1.82MPa)		°C	210
	(4.6kg/cm ²) (0.46MPa)		°C	-
其他性能	OTHER			
密度	Density	ASTM D792	g/cm ³	1.605
模收缩率	Mold Shrinkage	ASTM D955		-
	横向	Normal	%	1
	纵向	Parallel	%	0.38
含水率	Moisture Contents	-	%	-
耐燃性	Flammability	UL-94	1.6mm	V0
		UL-94	3.2mm	-
附注	REMARK			
(1) 本物性表为典型测试值, 仅供参考, 不作为正式质保承诺。				