



# NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399  
http://www.nytex.com.tw

## Product Information

## NYLOY® NG-0830B

• Nylon 6 • 30% Glass Fiber Reinforced • Black

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	kg/cm <sup>2</sup> (MPa)	1450 (142.3)
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	kg/cm <sup>2</sup> (MPa)	2080 (204.12)
Flexural Modulus	ASTM D790	kg/cm <sup>2</sup> (MPa)	9.61x10 <sup>4</sup> (9430.81)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	9.5 (93.14)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-116
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm <sup>2</sup> ) (1.82MPa)		°C	210
(4.6kg/cm <sup>2</sup> ) (0.46MPa)		°C	-
<b>OTHER</b>			
Density	ASTM D792	g/cm <sup>3</sup>	1.350
Mold Shrinkage	ASTM D955		-
Normal		%	1.08
Parallel		%	0.39
Moisture Contents	-	%	-
<b>REMARK</b>			
<sup>(1)</sup> This data is for reference only.			