



# NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399  
http://www.nytex.com.tw

## Product Information

## NYLOY<sup>®</sup> PG-0030N

● PP ● 30% Glass Fiber Reinforced ● Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	kg/cm <sup>2</sup> (MPa)	760 (74.58)
Elongation	ASTM D638	%	3
Flexural Strength	ASTM D790	kg/cm <sup>2</sup> (MPa)	1080 (105.99)
Flexural Modulus	ASTM D790	kg/cm <sup>2</sup> (MPa)	5.35x10 <sup>4</sup> (5250.257)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	7.6 (74.51)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-97
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm <sup>2</sup> ) (1.82MPa)		°C	147
(4.6kg/cm <sup>2</sup> ) (0.46MPa)		°C	158
<b>OTHER</b>			
Density	ASTM D792	g/cm <sup>3</sup>	1.12
Mold Shrinkage	ASTM D955		-
Normal		%	1
Parallel		%	0.63
Flammability	UL-94	3.2mm	HB
<b>REMARK</b>			
(1) This data is for reference only.			