



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] D-0400N

- PC/ABS
- High Impact
- Natural

| PROPERTY | METHOD | UNIT | RESULT |
|--------------------------------------|------------|--------------------|-----------|
| MECHANICAL | | | |
| Tensile Strength | ASTM D638 | psi | 8250.36 |
| Elongation | ASTM D638 | % | 54 |
| Flexural Strength | ASTM D790 | psi | 12233.29 |
| Flexural Modulus | ASTM D790 | psi | 341394.03 |
| IZOD Impact, Notched 1/8" 73.4°F | ASTM D256 | ft-lb/in | 10.64 |
| IZOD Impact, Notched 1/8" -4°F | ASTM D256 | ft-lb/in | 5.14 |
| Hardness Rockwell R Scale | ASTM D785 | - | - |
| Hardness Shore D | ASTM D2240 | - | D-82 |
| THERMAL | | | |
| Heat Deflection Temp | ASTM D648 | | |
| 264 psi | | °F | - |
| 66 psi | | °F | 257 |
| OTHER | | | |
| Density | ASTM D792 | lb/in ³ | 0.0353 |
| Mold Shrinkage | ASTM D955 | | - |
| Normal | | % | 0.73 |
| Parallel | | % | 0.66 |
| Moisture Contents | - | % | - |
| REMARK | | | |
| (1) This data is for reference only. | | | |