



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] D-0700N

- PC/ABS
- High Impact
- Natural

| PROPERTY | METHOD | UNIT | RESULT |
|--------------------------------------|------------|--------------------------|---------------------------------|
| MECHANICAL | | | |
| Tensile Strength | ASTM D638 | kg/cm ² (MPa) | 510 (50.05) |
| Elongation | ASTM D638 | % | 35 |
| Flexural Strength | ASTM D790 | kg/cm ² (MPa) | 790 (77.53) |
| Flexural Modulus | ASTM D790 | kg/cm ² (MPa) | 2.20 x10 ⁴ (2158.98) |
| IZOD Impact, Notched 1/8" 23°C | ASTM D256 | kg-cm/cm (J/M) | 52 (509.8) |
| IZOD Impact, Notched 1/8" -20°C | ASTM D256 | kg-cm/cm (J/M) | 35 (343.14) |
| Hardness Rockwell R Scale | ASTM D785 | - | - |
| Hardness Shore D | ASTM D2240 | - | D-82 |
| THERMAL | | | |
| Heat Deflection Temp | ASTM D648 | | |
| (18.6kg/cm ²) (1.82MPa) | | °C | - |
| (4.6kg/cm ²) (0.46MPa) | | °C | 125 |
| OTHER | | | |
| Density | ASTM D792 | g/cm ³ | 1.14 |
| Mold Shrinkage | ASTM D955 | | - |
| Normal | | % | 0.65 |
| Parallel | | % | 0.54 |
| Moisture Contents | - | % | - |
| REMARK | | | |
| (1) This data is for reference only. | | | |