



耐特 NYTEX COMPOSITES CO., LTD. 科技材料股份有限公司

Product Information

NYLOY® UG-8030N-V 10T NL

- PA10T • 30% glass fiber reinforced / halogen free flame retardant
- Natural

PROPERTIES	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	135
Elongation	ISO 527	%	2.0
Flexural Strength	ISO 178	MPa	200
Flexural Modulus	ISO 178	MPa	9200
Charpy Impact, Notched 23° C	ISO 179/2-1eU	kJ/m ²	7.5
Charpy Impact, Notched -30°C	ISO 179/2-1eU	kJ/m ²	7.0
Hardness Rockwell R Scale	ISO 2039	-	-
THERMAL			
Heat Deflection Temp 1.8 MPa	ISO 75	°C	300
OTHER			
Specific Gravity	ISO 1183	g/cm ³	1.40
Mold Shrinkage	ISO 294		
Normal		%	-
Parallel		%	-
Flammability	UL-94	0.4mm	V0
REMARK			
(1)This data is for reference only .			

Moulding guide

Drying Temp.	°C	100~120
Drying Time	hr	4~12
Mold Temp.	°C	125~145
1 st inj.		
V(%)/P(%)	%	75/65
2 nd inj.		
V(%)/P(%)	%	65/55
3 rd inj.		
V(%)/P(%)	%	55/45
4 th inj.		
V(%)/P(%)	%	35/20
Nozzle Temp.	°C	325~335
1 st Barrel Temp.	°C	330~340
2 nd Barrel Temp.	°C	325~335
3 rd Barrel Temp.	°C	305~315
Cooling Time	Sec.	16

REMARK

This data-sheet is for reference only.