



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] UB-0010N G35N4N

• High Temp. Nylon • Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	190
Tensile Modulus	ISO 527	MPa	-
Elongation	ISO 527	%	2.5
Flexural Strength	ISO 178	MPa	280
Flexural Modulus	ISO 178	MPa	10200
Charpy Impact, Notched 23° C	ISO 179	kJ/M ²	10
THERMAL			
Heat Deflection Temp (18.6kg/cm ²)(1.82MPa)	ISO 75	°C	270
OTHER			
Ash Contents	ISO 3451	%	GF 35
Flammability	UL-94	1.6mm	-
	UL-94	0.8mm	-
Density	ISO 1183	g/cm ³	1.44
PHYSICAL			
Mold Shrinkage	ISO 294-4		-
Normal		%	1.1
Parallel		%	0.41
FLAMMABILITY			
Glow Wire Test(GWFI)	IEC 60695-2-12	2.0mm	-
Glow Wire Test(GWIT)	IEC 60695-2-13	2.0mm	-
REMARK			
(1)This data is for reference only.			