



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] N-0020N-V0

- Nylon6
- Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	10668.56
Elongation	ASTM D638	%	10
Flexural Strength	ASTM D790	psi	15647.23
Flexural Modulus	ASTM D790	psi	426744
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	0.74
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	-
66 psi		°F	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
OTHER			
Density	ASTM D792	lb/in ³	0.0363
Mold Shrinkage ⁽²⁾	ASTM D955	%	0.7~1.4
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	V2
	UL-94	1/8 in	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			