



# NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399  
http://www.nytex.com.tw

## Product Information

## NYLOY® PG-0220B

● PP ● Glass Fiber Reinforced ● Black

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi	7112.38
Elongation	ASTM D638	%	4
Flexural Strength	ASTM D790	psi	11379.8
Flexural Modulus	ASTM D790	psi	419631.6
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.2
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
264 psi		°F	-
66 psi		°F	-
<b>ELECTRICAL</b>			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
<b>OTHER</b>			
Density	ASTM D792	lb/in <sup>3</sup>	0.0332
Mold Shrinkage <sup>(2)</sup>	ASTM D955	x10 <sup>-3</sup> mm/mm	0.3~0.5
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	-
	UL-94	1/8 in	-
<b>REMARK</b>			
<sup>(1)</sup> This data is for reference only.			
<sup>(2)</sup> Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			