



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] MG-0013N

- Nylon 66 • 13%Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	14224.75
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	psi	23470.84
Flexural Modulus	ASTM D790	psi	682788.05
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.28
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	0
Hardness Rockwell R Scale	ASTM D785	-	R-110
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	437
66 psi		°F	-
OTHER			
Density	ASTM D792	lb/in ³	0.0379
Mold Shrinkage	ASTM D955		-
Normal		%	1.43
Parallel		%	0.74
Moisture Contents	-	%	-
REMARK			
(1) This data is for reference only.			