



# NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399  
http://www.nytex.com.tw

## Product Information

## NYLOY<sup>®</sup> MG-0013N

• Nylon 66 • 13%Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ISO 527	MPa	115
Elongation	ISO 527	%	3
Flexural Strength	ISO 178	MPa	175
Flexural Modulus	ISO 178	MPa	4400
Charpy Impact, Notched 23° C	ISO 179/ 1eA	kJ/m <sup>2</sup>	6
Charpy Impact, Notched -20° C	ISO 179/ 1eA	kJ/m <sup>2</sup>	-
Hardness Rockwell R Scale	ISO 2039	-	R-110
Hardness Shore D	ISO 868	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ISO 75		
1.82MPa		°C	220
0.46MPa		°C	-
<b>OTHER</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.21
Mold Shrinkage	ISO 294-4		-
Normal		%	1.43
Parallel		%	0.74
Ash Content	-	%	13
<b>REMARK</b>			
(1) This data is for reference only.			