



# NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399  
http://www.nytex.com.tw

## Product Information

## NYLOY<sup>®</sup> MG-0023N

• Nylon 66 • 23%Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi	20625.89
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	psi	32716.93
Flexural Modulus	ASTM D790	psi	1009957.33
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.93
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	0
Hardness Rockwell R Scale	ASTM D785	-	R-112
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
264 psi		°F	464
66 psi		°F	-
<b>OTHER</b>			
Density	ASTM D792	lb/in <sup>3</sup>	0.0403
Mold Shrinkage	ASTM D955		-
Normal		%	1.31
Parallel		%	0.51
Moisture Contents	-	%	-
<b>REMARK</b>			
(1) This data is for reference only.			