



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] MG-0235B-2

- Nylon 66
- 35%Glass Fiber Reinforced
- Black

| PROPERTY | METHOD | UNIT | RESULT |
|--------------------------------------|------------|--------------------|------------|
| MECHANICAL | | | |
| Tensile Strength | ASTM D638 | psi | 21763.87 |
| Elongation | ASTM D638 | % | 2 |
| Flexural Strength | ASTM D790 | psi | 30583.21 |
| Flexural Modulus | ASTM D790 | psi | 1351351.35 |
| IZOD Impact, Notched 1/8" 73.4°F | ASTM D256 | ft-lb/in | 1.89 |
| IZOD Impact, Notched 1/8" -4°F | ASTM D256 | ft-lb/in | - |
| Hardness Rockwell R Scale | ASTM D785 | - | R-116 |
| Hardness Shore D | ASTM D2240 | - | - |
| THERMAL | | | |
| Heat Deflection Temp | ASTM D648 | | |
| 264 psi | | °F | 464 |
| 66 psi | | °F | - |
| OTHER | | | |
| Density | ASTM D792 | lb/in ³ | 0.0437 |
| Mold Shrinkage | ASTM D955 | | - |
| Normal | | % | 1.1 |
| Parallel | | % | 0.41 |
| Moisture Contents | - | % | - |
| REMARK | | | |
| (1) This data is for reference only. | | | |