



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] MG-1014NM

- Nylon 66
- 14% Glass Fiber Reinforced/Impact Modified
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	73
Elongation	ISO 527	%	10
Flexural Strength	ISO 178	MPa	113
Flexural Modulus	ISO 178	MPa	3520
Charpy Impact, Notched 23° C	ISO 179/ 1eA	kJ/m ²	25
Charpy Impact, Notched -20° C	ISO 179/ 1eA	kJ/m ²	-
Hardness Rockwell R Scale	ISO 2039	-	R-114
Hardness Shore D	ISO 868	-	-
THERMAL			
Heat Deflection Temp	ISO 75		
1.82MPa		°C	-
0.46MPa		°C	-
OTHER			
Density	ISO 1183	g/cm ³	1.17
Mold Shrinkage	ISO 294-4		-
Normal		%	1.31
Parallel		%	1.11
Ash Content	-	%	14
REMARK			
(1) This data is for reference only.			