



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] MG-1113B

- Nylon 66
- 13% Glass Fiber Reinforced/Impact Modified
- Black

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	730 (71.64)
Elongation	ASTM D638	%	3
Flexural Strength	ASTM D790	kg/cm ² (MPa)	1130 (110.89)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	3.70x10 ⁴ (3631.01)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	15.5 (151.96)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-94
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	195
(4.6kg/cm ²) (0.46MPa)		°C	-
OTHER			
Density	ASTM D792	g/cm ³	1.172
Mold Shrinkage	ASTM D955		-
Normal		%	1.08
Parallel		%	0.78
Moisture Contents	-	%	-
REMARK			
(1) This data is for reference only.			