



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] M-0010N-V0

- Nylon 66
- Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	620 (60.84)
Elongation	ASTM D638	%	26
Flexural Strength	ASTM D790	kg/cm ² (MPa)	1000 (98.14)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	2.90x10 ⁴ (2845.93)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	10.5 (102.94)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	D-77
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	-
(4.6kg/cm ²) (0.46MPa)		°C	-
OTHER			
Density	ASTM D792	g/cm ³	1.274
Mold Shrinkage	ASTM D955		-
Normal		%	1.55
Parallel		%	1.49
Moisture Contents	-	%	-
Flammability	UL-94	1.6mm	V0
	UL-94	3.2mm	-
REMARK			
(1) This data is for reference only.			