



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] MG-2012N-V0

- Nylon 66
- 12% Glass Fiber Reinforced/Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	15931.72
Elongation	ASTM D638	%	2.7
Flexural Strength	ASTM D790	psi	23470.84
Flexural Modulus	ASTM D790	psi	793741.11
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.38
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	R-117
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	410
66 psi		°F	-
OTHER			
Density	ASTM D792	lb/in ³	0.0463
Mold Shrinkage	ASTM D955		-
Normal		%	1.13
Parallel		%	0.61
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	V0
	UL-94	1/8 in	-
REMARK			
(1) This data is for reference only.			