



NYTEX COMPOSITES CO., LTD.

TEL:02-26963366 FAX:02-26963399
http://www.nytex.com.tw

Product Information

NYLOY[®] NG-0013N

• Nylon 6 • 13% Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	110
Elongation	ISO 527	%	3.2
Flexural Strength	ISO 178	MPa	170
Flexural Modulus	ISO 178	MPa	4300
Charpy Impact, Notched 23° C	ISO 179/ 1eA	kJ/m ²	6
Charpy Impact, Notched -20° C	ISO 179/ 1eA	kJ/m ²	-
Hardness Rockwell R Scale	ISO 2039	-	R-108
Hardness Shore D	ISO 868	-	-
THERMAL			
Heat Deflection Temp	ISO 75		
1.82MPa		°C	190
0.46MPa		°C	-
OTHER			
Density	ISO 1183	g/cm ³	1.21
Mold Shrinkage	ISO 294-4		-
Normal		%	1.01
Parallel		%	0.49
Ash Content	-	%	13
REMARK			
(1) This data is for reference only.			